



SPECIFICATION

<p>RADIANT COATING OKITSUMO COOLTECH CT-800 Black</p>
--

ADAPT TEMP. : 600 - 1000	DRYING : Baking	1 coat type
COLOR : Black	Mat Less type	PACKING : 1 Liquid type

CARACTERISTIC

It is superior in radiation in use at high temperature area.
There are three colors as black, white, and gray.

APPLICATION

Stainless steel

COATING METHOD

SURFACE PREPARATION		Degreasing or blast
WAY OF COATING		Spray or electrostatic coating
HARDENER [Usable time]		1 wt% [72hrs]
DILUENT	Spray	50, 100, 500 thinner
	Electrostatic	0.6, 0.7, 0.8 thinner
DILUTION	Spray	5 - 15 wt%
	Electrostatic	10 - 50 wt%
THICKNESS (DRY)		10 - 20 μ m
COATING TIMES		1 time
SUITABLE AMOUNT		110g/m ² /time
PRE-DRYING		80 - 160 \times 10mins.
DRYING		380 \times 20mins.

* For repair, remove the dust with sand paper (#600-#1000), then recoat and baking.

PACKING 1Kg, 4Kg, 16Kg