



Specification

Date : 2007.8.28

Revised :

Okitsumo Heat Resistant Paint No.605 Silver

Painting by brush

Process	Product Name	Diluent	Dilution (wt%)	Coverage (g/m ² /pass)	Film thickness Dry (μm)	Interval (20)
1	Appropriate substrate	Aluminium, iron , stainless				
2	Pre-treatment	Over SSPC-SP3/SIS St3 (by hand tool, machine tool or blast)				
3	Painting (1 pass)	No.605 Silver	No.50 No.100 thinner	0 ~ 10	75	10

Painting by airless

Process	Product Name	Diluent	Dilution (wt%)	Coverage (g/m ² /pass)	Film thickness Dry (μm)	Interval (20)
1	Appropriate substrate	Aluminium, iron, stainless				
2	Pre-treatment	Over SSPC-SP3/SIS St3 (by hand tool, machine tool or blast)				
3	Painting	No.605 Silver	No.50 No.100 thinner	0 ~ 10	100	10

[Drying]

Drying at room temp. make the film set to touch. Harden at 180 for 20mins by baking.