



SPECIFICATION

Okitsumo HEAT RESISTANT PAINT

ONE TOUCH SPRAY MAT BLACK

HEAT RESISTANCE : 650°C(*1)	DRY : at Normal temp. or baking	CONSTRUCTION: 1 Coat
COLOR: Black	GLOSS: Mat type	APPEARANCE : Aerosol

CARACTERISTIC

Easy to coat

APPLICATION

Aluminum, Iron, Stainless (*1) Heat resistant temperature changes with materials.

USE

Repair heater, outside of incinerator and smokestack, heating parts.

HOW TO

PREPARATION	Remove the rust, stain and oil on the surface (*2)	
ARRANGE 1	Cover the parts you don't need spray with news paper or masking tape in advance.	
ARRANGE 2	Shake the spray can until you can hear the marble inside.	
ARRANGE 3	At first, check if there are no problems such as color, spray condition, drying, effect on the material and adhesion by trial coating. (Color of indication differs from actual color more or less)	
COATING	Set nozzle apart from paint surface 30 - 40cm, then spray. At that time, don't spray it thickly, move the spray can in parallel and spray it thinly.	
FILM THICKNESS (Dry)	10 − 20 <i>μ</i> m	
COATING TIMES	1 Time	
STANDARD COATING AREA	1.5 - 2.0m² (*4)	
DRYING	Over 24hrs (*4,*5) or 180°Cx 20 - 30mins	
AFTER USE	Turn the spray can upside down, spray until empty, then wipe the nozzle hole.(*6)	

Okitsumo Incorporated 1109-7 SHIBADE, KURAMOCHI-CHO, NABARI-CITY MIE 518-0751 JAPAN

TEL: +81-595-64-4124 FAX: +81-595-64-1289



technical information

P2/5-A17

- (*2)Polish the detect parts on the surface with sand paper (#600 #1000), clean it by air-blow then spray it. (Don't spray when the surface temperature is high.
- (*3)When air temp. goes down, the paint doesn't come out well. So please immerse into lukewarm water (30°C) for 3 5mins., then use it.
- (*4)Depending on color, material, shape, how to coat and weather, coated area and drying time changes.
- (*5)The film after coat has not reached to perfection hardening with dry to touch. Depending on work, it has stickiness and smokes temporarily, but the smoke stops and the film hardens. (As a standard, it has not reached to perfection hardening until teat it at 180°C for over 20 30mins.)
- (*6)To prevent the paint plugging up from the inside of nozzle and tube of spray can until next use. If plug up the nozzle, clean with it with tinner.

PACKING

300ml

Okitsumo Incorporated 1109-7 SHIBADE, KURAMOCHI-CHO, NABARI-CITY MIE 518-0751 JAPAN TEL: +81-595-64-4124 FAX: +81-595-64-1289